Jalcover 12

5.2 OZ GEOMEMBRANE



Multilayered Geomembrane



A medium weight fabric incorporating a new coating recipe designed to improve toughness and abrasion resistance.

RECOMMENDED APPLICATIONS

Grain Covers, Temporary Landfill Covers, Short-term Liners

PRODUCT DIMENSIONS

Cores 4 inch I.D. or 5 inch I.D. available
Width Up to 144 inches (-0, +0.25) as ordered
Length Minimum 500 yds/roll; up to 1000 yds/roll

PRODUCT SPECIFICATIONS

Weave Woven black HDPE scrim

Coating LDPE, 1.75 mil average each side (41.5 g/m²/side)

Color Black or colored coatings available

Weight 5.2 oz/yd² (176g/m²) \pm 5 %

These values are typical data and are not intended as limiting specifications.



Jalcover 12

5.2 OZ GEOMEMBRANI



Multilayered Geomembrane

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Thickness ASTM D1777	Nominal 12mil (0.30mm) ± 10%
Grab Tensile (N) ASTM D7004	MD 180 lb (800) TD 125 lb (555)
Strip Tensile (N/5cm) ASTM D7003	MD 140 lb/in (1243) TD 100 lb/in (888)
Tongue Tear-large scale (N) ASTM D5884	MD 50 lb/in (222) TD 50 lb/in (222)
Mullen Burst ASTM D751	275 psi (1894 kPa)
MVTR ASTM E96 Proc. BW	0.42 g/m² • 24hr (0.06perms)
Hydraulic Conductivity (Permeability) Calculated from MVTR	0.88 x 10 ⁻¹² cm/s
Hydrostatic Resistance ASTM D751	130 psi (900 kPa)
Puncture Resistance ASTM D4833	76 lb (338 N)
Dimensional Stability ASTM D1204	MD -3.60% TD -2.42%
Carbon Black Content ASTM D4218	2.79%
Low Temperature Flex ASTM D2136	MD&TD: Pass @ -40°C (-40°F)
Accelerated UV Weathering* ASTM G151 ASTM G154	>90% tensile strength retention after 2,000 hrs exposure @ 0.77 W/m²/nm, or 1200 hours exposure @ 1.35 W/m²/nm

MD = Machine Direction. TD = Tensile Direction

These values are typical data and are not intended as limiting specifications.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



^{*} Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4hrs condensation @ 50°C