

Technical Data of Raptor Underlayment

<u>Property</u>	<u>Value</u>	<u>Test Method</u>
Thickness	8 mills	
Unrollability	Pass	AC 188
Pliability	Pass	ASTM D 226
Tensile Strength	MD: 75 lbf/ CD: 39 lbf	ASTM D 1970
Ultraviolet Exposure	Pass	AC48/AC188
Accelerated Aging	Pass	AC48/AC188
Liquid Water Transmission	Pass	ASTM D4869
Water Vapour Transmission	0.061 (g/m ² /hr)	ASTM E96
Nail Pull Through Resistance	MD 32 lbf/ CD 28 lbf	ASTM D3462
Staple Pull Through Resistance	MD 20 lbf/ CD 21 lbf	ASTM D3462
Recommended exposure limit	6 Months	
Fire Characteristics		Class A

Construction	8 x 4
Width per roll	48" / 122cms
Length per roll	250' / 76.2 m
Weight per roll	25 lbs
Roll Size	10sq / 93 m ²
Rolls per pallet	56 nos
Pallet Weight (56 rolls)	1400 lbs